



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C08K 5/13, 5/09</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/52978</b> <b>(43) International Publication Date:</b> 21 October 1999 (21.10.99)
<b>(21) International Application Number:</b> PCT/US99/06768 <b>(22) International Filing Date:</b> 29 March 1999 (29.03.99)  <b>(30) Priority Data:</b> 06/081,144 9 April 1998 (09.04.98) US  <b>(71) Applicant:</b> E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). <b>(72) Inventor:</b> SOELCH, Richard, Robert; 139 Cambridge Road, Landenberg, PA 19350 (US). <b>(74) Agent:</b> PHAM, Hanh, T.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		<b>(81) Designated States:</b> CA, CN, JP, KR, SG, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> LOW VISCOSITY LIQUID CRYSTALLINE POLYMER COMPOSITIONS  <b>(57) Abstract</b>  Liquid crystalline polyesters or poly(ester-amides) having improved melt viscosity, are made by reacting the polymer with limited amounts of a compound containing specified functionality, such as hydroxyl, carboxyl, or amine. The process may be carried out in a typical polymer melt mixing apparatus such as an extruder. The low viscosity polymer product of the claimed invention has surprising toughness and is particularly useful for encapsulation of electronic components.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Title

## LOW VISCOSITY LIQUID CRYSTALLINE POLYMER COMPOSITIONS

BACKGROUND5    Field of the Invention

The present invention relates to improved melt-flow liquid crystalline polymer compositions (LCPs) with unusually high toughness.

Background of the Invention

10    Liquid crystalline polymer compositions are known in the art by various terms, including "liquid crystal" and "anisotropic melts." LCPs are known to have exceptionally high tensile strength and modulus compared to analogous polymers not having a liquid crystalline character. LCPs are useful in many applications, including molding resins for a variety of electrical parts, and for other uses such as films. While LCPs are known for their ability to flow under difficult molding conditions, in some  
15    instances such as for encapsulating electronic components, the melt viscosities of normal molding grade LCPs are too high.

Generally speaking, the melt viscosity of any given LCP is most affected by the polymer molecular weight, the lower the molecular weight the lower the melt viscosity. While low molecular weight LCPs can be synthesized directly by  
20    condensation polymerization, this method may have some drawbacks. The polymer produced may have a tendency to increase in molecular weight (MW) during melt processing by continuation of the melt condensation process. At extremely low viscosity levels of 50 Pa\*s or less, these LCPs are very brittle. Additionally, the handling of such low molecular weight polymers in processes designed to produce  
25    molding grade polymers can be problematical.

European Patent Application 376,615 describes a method of preparing a LCP with a relatively low melt viscosity by mixing 100 parts of a high molecular weight LCP with 1 - 100 parts, preferably 10 - 40 parts, of a low molecular weight LCP with a MW about 1000 to 7000, preferably between 1000 - 4000. This method requires  
30    production of an unusual low molecular weight LCP using special equipment, since the low molecular weight LCP material is not readily commercially available at a MW range of 1000 to 7000.

U.S. Patent No. 4,434,262 describes an improved melt processable blend of a major amount of polyester or polyolefin with a low MW liquid crystalline compound preferably below 1000 molecular weight. The liquid crystalline compound does not chemically react with the polyolefin or the polyester component in the melt blend.

5 Melt viscosity reductions of 25% to 75% were obtained by adding 10 parts by weight of the liquid crystalline compound to 90 parts by weight of polyolefin or polyester.

Accordingly, it is an object of this invention to provide a method for improving the melt viscosity or fluidity of an LCP, as well as an LCP resin composition having improved melt-viscosity, or fluidity, that can be efficiently  
10 fabricated into an article having a small thickness or an intricate shape at lower processing temperatures, while still maintaining the original strength, rigidity, and elongation characteristics of the parent LCP.

### SUMMARY OF THE INVENTION

A composition having improved fluidity and excellent toughness  
15 characteristics, comprising: a thermotropic liquid crystalline polymer and about 5 to about 250 milli equivalents of the liquid crystalline polymer, of a functional compound per kilogram whose functionality is selected from the group consisting of hydroxyl, carboxyl, carboxylate, ester, and primary or secondary amine.

The invention also relates to a practical method for the production of a lower  
20 melt-viscosity thermotropic liquid crystalline polymer by combining under reaction conditions, the liquid crystalline polymer with a functional compound, at a ratio of about 5 to about 250 milli equivalents of functional compound per kilogram of the liquid crystalline polymer. The functional compound is selected from the group consisting of hydroxyl, carboxyl, carboxylate, ester, and primary or secondary amine.

25 The present invention further relates to a method for improving the fluidity of a liquid crystalline polymer by combining the liquid crystalline polymer with about 5 to about 200 milli equivalents per kilogram of said liquid crystalline polymer of a functional compound, whose functionality is selected from the group consisting of hydroxyl, carboxyl, carboxylate, ester, and primary or secondary amine, at a  
30 temperature sufficient to cause reaction of said functional compound with said liquid crystalline polymer, and for a period of time sufficient to cause at least a 10%

lowering of a melt viscosity of said liquid crystalline polymer when measured at a shear rate of 1000 sec<sup>-1</sup>.

## DETAILS OF THE INVENTION

### LCP Component

5 Thermotropic liquid crystalline polymers are known in the art by various terms, including "liquid crystal" and "anisotropic melts." Liquid crystalline polymers are prepared from monomers which are generally long, flat, and fairly rigid along the axis of the molecule and have chain extending linkages that are either coaxial or parallel. Whether or not a polymer is in a liquid crystal state can be determined by  
10 known procedures for determining optical anisotropy. A polymer is optically anisotropic if, in the melt phase, it transmits light when examined between crossed polarizers utilizing a polarizing microscope. A thermotropic liquid crystalline polymer herein is given its conventional meaning, is an LCP by the TOT test described in U.S. Patent 4,075,262, which is hereby included by reference. The LCP polymers useful  
15 herein include polyesters, poly(ester-amides), poly(ester-imide), poly(ester-amide-imide), polyazomethines, or mixtures thereof. Any thermotropic LCP may be used in these compositions and processes.

Preferred thermotropic LCPs are polyesters or poly(ester-amides), and it is especially preferred that the polyester or poly(ester-amide) is partly or fully aromatic.  
20 By aromatic polyesters is meant that the carbon atom and oxygen atom, **-C(O)O-** (bolded in this formula), of the ester linkages, are bonded to carbon atoms which are part of aromatic rings.

### Functional Compounds

The functional compounds used herein may be mono-, di-, trifunctional, etc.  
25 The functionality for any particular functional compound should preferably be the same functional group if more than one functional group is present. It is also preferred that the functional group is bound directly to a carbon atom of an aromatic ring. More than one functional compound may be used, so long as the total amount of functional compound added is within the range of about 5 to about 250 milli  
30 equivalents per kilogram (meq/kg) of LCP. The functional compound may contain other substituents, so long as these substituents do not interfere with the process of reducing the LCP viscosity.

Useful functional compounds include hydroquinone, 1-naphthol, bisphenol-A, 1,6-hexanediaminecarbamate, terephthalic acid, trimesic acid, 2,6-naphthalene dicarboxylic acid, 1-napthoic acid, sodium benzoate, dimethyl terephthalate, hydroquinone diacetate, 6-hydroxy-2-napthoic acid, 4-aminophenol, 5 hexamethylenediammonium adipate, 1,4-cyclohexanedicarboxylic acid, cyclohexanoic acid, 1,12-dodecanedicarboxylic acid, 4,4'-biphenol, 1,6-hexanediamine, 4-sulfoisophthalic acid, and isophthalic acid. The preferred functional groups are hydroxyl and amine, with hydroxyl and carboxyl being particularly preferred because they are surprisingly more effective at reducing 10 viscosity on an equivalent basis. The preferred functional compounds are mono-functional or di-functional, with di-functional being more preferred. However, if it is desired to also introduce branching or crosslinking into the LCP while lowering its viscosity, tri- or higher functional compounds are used. Preferably, the functional compound has a molecular weight of about 100 to about 300 grams per mole.

15 Besides the useful functional compounds listed above, compounds that readily generate the appropriate functional groups in the list for reducing the LCP viscosity are also included within the definition of useful groups. For instance, amine carbamates generally readily decompose thermally to their respective amines, and are therefore considered herein as amines.

20 An important factor in the choice of the functional compound is its volatility. While relatively volatile compounds may be used, it is preferred that the functional compound chosen to be not too volatile, having low vapor pressure at the process conditions. While not fatal to the process of lowering the melt viscosity, any vaporization of a relatively volatile functional compound represents a yield loss and 25 reduces the "practical efficiency" of the functional compound in lowering viscosity in a conventional extruder. If the compound is relatively volatile, precautions should be taken to prevent loss by volatilization or some of the functional compound will be "lost" to the air.

It is preferred that about 25 to about 125 meq/kg of LCP of the functional 30 compound be used. By equivalents herein is meant the number of "moles" of functional group (e.g., hydroxyl, etc.) added to the process or composition.

#### Other Components

The low-melt viscosity LCP compositions of the present invention may optionally have in them other types of ingredients without detriment to the fluidity or physical properties of the LCP, such as fillers, reinforcing agents, pigments, lubricants, mold releases, antioxidants, and other materials usually found in thermoplastic compositions.

#### Preparation

In order to reduce the viscosity of the LCP, it is necessary to reasonably uniformly mix the functional compound with the starting LCP. This may be done by melt mixing the LCP and functional compound before or simultaneous with the step of exposing the mixture to temperatures at which reaction occurs between the functional compound and the ester groups of the LCP. This is most conveniently done by carrying out the process in a typical polymer melt mixing apparatus, such as a single or twin screw extruder or a kneader. This type of a process releases few if any emissions to the environment.

The novel composition may be made by simply dry blending particles (such as pellets) of the LCP and powder or liquid of the functional compound in the appropriate relative amounts. The dry blending may be done by tumble blending. The blended mixture may then be fed to an appropriate melt mixer. Alternatively, the polymer, usually in the form of pellets, and the functional compound may be separately metered into the melt mixing apparatus and mixed therein while the polymer (and perhaps the functional compound) is being melted.

In order to carry out the reaction for lowering the melt viscosity, the temperature should be above the melting point of the LCP. This temperature typically ranges from about 200°C to about 400°C melt temperature, preferably about 275°C to about 360°C. Depending on the temperature, the functional compound, and the LCP used, useful reductions in melt viscosity can typically be obtained in about 30 sec to about 10 minutes, preferably about 45 sec to about 3 minutes. This time range is typical of residence times in a polymer melt mixing apparatus.

The ingredients of the claimed composition are usually added by melt mixing in any of the following stages:

1. Adding the ingredients after the viscosity of the LCP is reduced. The melt viscosity reduction of the LCP is measured by comparing the viscosity of

the "pure" LCP before and after reaction with the functional compound, and before the ingredients are added.

2. Adding before and in a separate step from the viscosity reduction process. Viscosity reduction is measured based on the composition (including the added ingredients) before and after reaction with the functional compound.

3. Adding in the same operation as the viscosity reduction, i.e., the added ingredients are melt mixed at essentially the same time as the functional compound is mixed in and/or reacts with the polymer. This is preferred in many instances since the viscosity reduction and inclusion of the other ingredients can be accomplished in one step. Viscosity reduction is measured comparing the after viscosity with the before viscosity of a polymer containing the additional ingredients mixed in the same manner, but without the functional compound present.

The LCP composition with lowered viscosity may be pelletized or formed for later use in molding or extruding applications. Alternatively, the composition can be prepared directly in a molding machine to form molded parts.

#### Measurement of Melt Viscosity

The viscosity of the claimed LCP composition, when measured at a shear rate of 1000 sec<sup>-1</sup>, is lowered at least 10% from the original viscosity as shown below:

$$\text{Final visc.} \leq \text{Initial visc.} - 0.10(\text{Initial visc.})$$

In most cases, the final viscosity of the LCP is measured to be at least 50% less than the initial viscosity. In certain applications, the LCP composition of the present invention can be processed at temperature levels below that of the starting LCP. For most practical applications, viscosity reduction is preferably at least 50%. In some cases, the final viscosity is reduced by one or two orders of magnitude from the initial viscosity of the starting LCP. At this low viscosity level of about 10 Pa\*s or less, the final LCP is a thermoplastic with the low viscosity characteristic of a thermoset and can be used in thermoset applications such as encapsulation and composites.

The final viscosity of the LCP with improved fluidity of the invention is often found to be surprisingly stable in viscosity. Viscosity stability is an important factor



in commercial applications since some thermoplastics materials, i.e., sprues and runners, are routinely recycled. It is critical for the viscosity of the sprues and runners to remain stable for a reasonable period of melt processing time (15 minutes or more), allowing them to be mixed in with the virgin materials for recycle  
5 processing. Even with an improved fluidity, the final LCPs surprisingly retain the high strength, rigidity, and good elongation characteristics of the parent LCPs.

Melt viscosity of the Examples that follow was determined on a Kayeness rheometer (Kayeness, Inc., RD#3, Box 30, E. Main St., Honeybrook, PA 19344 U.S.A.). Generally, the Kayeness rheometer can readily and routinely measure melt  
10 viscosities down to about 50 Pa\*s and 1000 1/s. However, great care is needed to gauge viscosity below this value of 50 Pa\*s.

Melt viscosity of the Examples in Tables I and II was generated using a die having a hole radius of 0.5 mm (0.02") by 2.0 cm (0.80") long using a melt time of 360 sec. Melt viscosity of the Examples in Table III was generated using an  
15 experimental die with a die hole radius of 0.20mm (0.0078") by 3.48cm (1.2") long. This small diameter die was custom fabricated using commercially available EDM type drills. This small 0.20 mm die gives a more accurate measurement of viscosity under 10 Pa\*s than a 0.5 mm radius die and can measure viscosity levels of 0.4 Pa\*s with an accuracy of about  $\pm 0.1$  Pa\*s. For both dies, a preheating time of at least five  
20 minutes and preferably about thirty minutes is required in between samples (when measuring viscosity on multiple samples) to minimize variability in viscosity values.

At a viscosity level of about 20 Pa\*s at 1000 1/s and below, measuring viscosity is quite a challenge due to sample drooling from the die during the hold portions of the measurement test. The drooling can be effectively minimized by  
25 manually plugging the orifice during the preheat and in between measurements (multiple measurements are usually made within one Kayeness run).

At a viscosity level of about 10 Pa\*s, and especially below about 5 Pa\*s, the extremely fluid melt tends to seep in between the Kayeness piston and cylinder. The variability of these measurements may be reduced by making multiple measurements  
30 at one shear rate until a steady state viscosity is reached (indicating that no more melt is seeping between the piston and cylinder walls).

#### Examples

For the examples listed in Tables I and Table II, including the comparable Example A, the LCP polymer has a composition of hydroquinone / 4,4'-biphenol / terephthalic acid / 2,6-naphthalene dicarboxylic acid / 4-hydroxybenzoic acid / 6-hydroxy-2-naphthoic acid in the molar ratios 50/50/70/30/270/50. The LCP polymer has a melting point of 231°C as determined by ASTM D3414-82 at a heating rate of 25° C/min, and a heat deflection temperature (HDT) of 120°C as measured by ASTM D648 at 1.8 MPa. The LCP polymer can be made by methods readily available or well-known to those skilled in the art, for example, with the acetate ester of the hydroxyl group being condensed with the carboxylic acids in the monomers.

For Table III, the LCP polymer has a composition of hydroquinone / 4,4'-biphenol / terephthalic acid / 2, 6-naphthalenedicarboxylic acid / 4-hydroxybenzoic acid in the molar ratio of 50/50/70/30/320. This polymer may be prepared from the appropriate monomers by standard poly-condensation techniques well-known to those skilled in the art. When the polymerization appears nearly complete as indicated by the amount of by-product collected in this poly-condensation process, the molten mass is placed under vacuum and heated to a higher temperature to complete the polymerization and remove the remaining by-product.

The pre-polymer in Table III is a lower molecular weight version of the same composition as the LCP polymer and prepared essentially the same way, except that the polymerization process was cut short. The ingredients (967.6 grams) were combined with 765.3 mls of acetic anhydride and refluxed for 40 minutes at 170°C. Acetic acid was removed over the next three hours while the temperature was increased to 325°C. At this point, vacuum was applied gradually over the next 50 minutes to 50 mm and further to 1 mm after 20 more minutes, then held constant for an additional 85 minutes. The resulting brittle product is the pre-polymer in Table III.

The functional compounds used in the Examples are: terephthalic acid, 2,6-naphthalenedicarboxylic acid, dimethyl terephthalate, hydroquinone, hydroquinone diacetate, trimesic acid, 1-naphthoic acid, 2,6-dihydroxynaphthalene, 1-naphthol, bisphenol A, 6-hydroxy-2-naphthoic acid, and 4,4'-biphenol are all commercially and readily available from various places including laboratory supply houses. Hexamethylene diammonium adipate is available from Rhone-Poulenc or BASF.

Hexamethylene diamine carbamate (Diak® #1) is available from DuPont-Dow Elastomers, Wilmington, DE, U.S.A.

The LCP, in pellet form, was dry blended with the functionalized compound and then fed to the back of a Werner & Pfleiderer 28mm twin screw extruder. The extruder was run with the barrels operated at 200–300 rpm, and set to 290°C for the Examples in Tables I and II and 340°C for the Examples in Table III.

The strand exiting the extruder was water quenched and cut into pellets. The pellets were vacuum-dried overnight (600-1200 Pa, absolute, with a nitrogen bleed) at 80–100°C. In the cases where very low melt viscosity compositions were prepared, it was advantageous to use a 45° die on the extruder which angled the strand downward into the water quench bath and effectively prevented the melt from sticking to the die face.

Dried pellets were injection molded on a 171 g (6 oz.) HPM injection molding machine (HPM Corp. 200-TP 6.5-6.5 oz. Injection Molding Machine) from HPM Corp., at 820 Marion Rd., Gilead, OH 43338, U.S.A. The machine was equipped with a general purpose type screw. Barrel and nozzle temperatures were typically set at 290°C for the compositions and molds were water heated to 80–90°C.

Tensile strength and elongation was measured on 3.2 mm (1/8") thick tensile bars with a cross-head speed of 0.51 cm (0.2")/min according to ASTM D638-91. Strain gauges were used to accurately determine elongation.

Flexural modulus was measured on 1.6 mm (1/16") thick flexural bars according to ASTM D790-92.

The functional compounds used, and the results of the viscosity stability tests are shown in Table I with the final viscosity of the LCP with improved fluidity found to be surprisingly stable.

Table I

Example	Functional Compound		Visc. (Pa*s) at 300°C		Visc. (Pa*s) at 300°C, 500 s <sup>-1</sup> over time in minutes				
	Name	meq/kg	100 1/s	1000 1/s	6.2	9.3	12.9	16.5	20.1
Compare A	NONE USED	-	212	66	97	95	106	104	106
14	6-hydroxy-2-naphthoic acid	50	35	15	--	--	20.2	19	19
16	hydroquinone plus terephthalic acid	25	90	39	53	34	54	47	47

The functional compounds used, and the results of the viscosity and property tests are shown in Table II showing the final viscosity of the LCP being at least 50% less than the initial viscosity in most cases.

5

Table II

Example	Functional Compound		Tensile	Tensile	Flexural	Viscosity, 300°C, Pa*s	
	Name	meq/kg	Strength MPa	Elong. %	Modulus GPa	100 sec <sup>-1</sup>	1000 sec <sup>-1</sup>
Comp. A	none	-	153	2.8	9.6	212	66
1	hydroquinone	50	139	2.0	9.7	78	36
2	hydroquinone	100	123	2.3	10.2	17	4 <sup>b</sup>
3	hydroquinone	200 <sup>a</sup>	106	3.5	8.5	5 <sup>b</sup>	2 <sup>b</sup>
4	1-naphthol	100	138	2.1	9.6	9	6
5	bisphenol-A	100	143	2.0	9.1	63	18
6	Diak® #1	50	131	1.9	9.1	22	14
7	terephthalic acid	100	132	1.9	9.2	89	43
8	trimesic acid	66.7	148	2.5	9.4	130	38
9	2,6-naphthalene dicarboxylic acid	100	145	3.0	9.4	94	44
10	1-naphthoic acid	100	141	1.9	9.7	50	24
11	sodium benzoate	50	-	-	-	85	37
12	dimethyl terephthalate	100	143	2.2	10.3	97	42
13	hydroquinone diacetate	100	143	2.0	10.1	61	18
14	6-hydroxy-2-naphthoic acid	50	131	1.7	9.7	35	15
15	4-aminophenol	50	119	2.0	9.6	54	30
16	hydroquinone plus terephthalic acid	25	131	2.1	9.9	90	39
17	hexamethylene diammonium adipate	50	-	-	-	24	19

<sup>a</sup> A white, apparently crystalline substance (presumably hydroquinone) sublimed from the extruder vacuum port. Thus it appears likely that the actual amount of hydroquinone in the product was somewhat less than 200 meq/kg.

<sup>b</sup> Very low viscosity. A value below 5 Pa\*s is simply an indicator of very low viscosity.

Table III compares properties of a starting LCP with a pre-polymer and the LCP of the present invention, showing the surprising combination of toughness and low melt-viscosity characteristics of the novel LCP composition of the present invention. The LCP is surprisingly tough compared with a directly polymerized pre-polymer as evidenced by the easy strand formation upon extrusion, in spite of the fact that the melt viscosities of the two materials are quite similar. The strands of the final LCP were easily extruded and cut into pellets while the pre-polymer had to be handled on a belt and shattered upon cutting.

Additionally, the pre-polymer was very brittle and readily cryogenically ground to a fine powder with a hammer mill using liquid nitrogen, whereas the LCP of the present invention formed a fibrous material that continued to expand upon continuous grinding. This characteristic is reflected in the bulk density of the ground products of the pre-polymer and the LCP composition plus a functional compound group. The low density of the LCP composition as shown in the Table is indicative of its fibrous nature. Photographs comparing the ground products under 50X magnification verified the feathery, fibrous nature of the LCP composition of the present invention which contrasted sharply with the essentially particulate ground pre-polymer composition.

Table II

Example	Type Used	Functional Compound meq/kg	Extruded Strand Toughness	Ground Bulk Density g/cc	Melt Visc 1000sec <sup>-1</sup> Pa*s	
					300°C	320°C
Compare 18	LCP	-	Tough	-	64	No Flow
Compare 19	Prepolymer	-	Brittle	0.406	~ 1	7
20	LCP + 4,4'-biphenol	215	Tough	0.111	~ 1	6

As is apparent from the foregoing description, the materials prepared and procedures followed relate only to specific embodiments of the broad invention. While forms of the invention have been illustrated and described, modifications can be made without departing from the spirit and scope of the invention. Accordingly, it is not intended that the invention be limited thereby.

AD-6532

Title

## LOW VISCOSITY LIQUID CRYSTALLINE POLYMER COMPOSITIONS

CLAIMS

5           What is claimed is:

1.       A composition comprising:

- a.       a liquid crystalline polymer;
- b.       a functional compound whose functionality is selected from the group  
10           consisting of hydroxyl, carboxyl, carboxylate, ester, and primary or  
          secondary amine;

          said functional compound being from about 5 to about 250 milli equivalents  
per kg by weight of said liquid crystalline polymer.

2.       The composition of claim 1, wherein said polymer is a liquid crystalline  
15       polyester.

3.       The composition of claim 1, wherein said functional compound is hydroxyl.

4.       The composition of claim 1, which is capable of undergoing melt-processing  
20       at a temperature sufficient to cause reaction of said functional compound with said  
liquid crystalline polymer and for a sufficient period of time to cause at least a 10%  
lowering of viscosity of said liquid crystalline polymer when measured at a shear rate  
of 1000 sec<sup>-1</sup>.

25       5.       The composition of claim 4, which is capable of undergoing melt-processing  
at a temperature below 250°C.

6.       A molded article fabricated from the composition of claim 1.

30

AD-6532

7. A method for making a polymer blend, which comprises the steps:
- a. preparing a thermotropic liquid crystalline polymer component which is an aromatic polyester, poly(ester-amide), poly(ester-imide), poly(ester-amide-imide), or mixtures thereof; and
  - 5 b. contacting under reaction conditions said liquid crystalline polymer component with a functional compound whose functionality is selected from the group consisting of hydroxyl, carboxyl, carboxylate, ester, and primary or secondary amine at a level of about 5 to about 250 milli equivalents per kg of said thermotropic liquid crystalline polymer.
- 10 8. The method according to claim 7 wherein said functional compound is hydroxyl.
9. The method according to claim 11 wherein said reaction is carried out at a
- 15 temperature of about 200°C to about 400°C.
10. A method for decreasing the viscosity of a liquid crystalline polymer composition, comprising contacting a liquid crystalline polymer and a functional compound whose functionality is selected from the group consisting of hydroxyl,
- 20 carboxyl, carboxylate, ester, and primary or secondary amine at a level of about 5 to about 250 milli equivalents per kg of said liquid crystalline polymer, at a temperature sufficient to cause reaction of said functional compound with said liquid crystalline polymer and for a period of time sufficient to cause at least 10% the lowering of the melt viscosity of composition when measured at a shear rate of 1000 sec<sup>-1</sup>.

# INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/06768

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08K5/13 C08K5/09

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 679 284 A (H.KURITA) 21 October 1997 (1997-10-21) claims 1,7 ---	1-3,6-8
A	US 5 264 477 A (K.F.WISSBRUN ET AL.) 23 November 1993 (1993-11-23) claims 1,2 ---	1,2,6
A	US 4 172 059 A (K.E.ATKINS ET AL.) 23 October 1979 (1979-10-23) claim 1 ---	10
A	US 4 434 262 A (A.BUCKLEY ET AL.) 28 February 1984 (1984-02-28) cited in the application column 3, line 42 - line 63; claims 1,2; example 5 -----	1,2,5,10

☐ Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

### \* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

13 July 1999

Date of mailing of the international search report

22/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040. Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3016

Authorized officer

Angiolini, D



# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 99/06768

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5679284 A	21-10-1997	JP 7196895 A CA 2138728 A	01-08-1995 29-06-1995
US 5264477 A	23-11-1993	NONE	
US 4172059 A	23-10-1979	NONE	
US 4434262 A	28-02-1984	NONE	

